



## EPOXY COATING

# CHEM GRIP EPOXY

## FEATURES

- Two part catalyst-type epoxy coating
- Unmatched resistance to sun, salt and extreme heat
- Protects against corrosion, rust and abrasion
- Outstanding resistance to chemicals
- Ideal for use on wood, metal, concrete, fiberglass and polyester surfaces
- No VOCs
- Water is used for thinning and clean up
- Non-flammable

## PROPERTIES

**Appearance:** Hazy liquid, white when mixed

**Boiling point:** 400°F

**Specific gravity:** 1.04 gr/cc

**Non volatiles:** 95 %

**Solubility in water:** Soluble

**Flash point:** 228 °F

**Storage stability:** Keep away from direct sun light and open flames

**pH of liquid:** 9-10

**Flammability:** Combustible

**Packaging:** 4 x 1 gal Case  
5 gal pail

- Properties are typical and subject to usual manufacturing tolerances.

**CHEM GRIP EPOXY** is a water based epoxy coating used for patching and resurfacing many different types of surfaces. This 2 part catalyst-type epoxy is specially formulated for use on wood, metal, concrete, fiberglass and polyester surfaces. It is extremely durable and strong as it protects against corrosion, rust and abrasion. It also has an outstanding resistance to chemicals and protects against acids, alkalis, caustics, fuels, sewage brine, oils and greases. **CHEM GRIP EPOXY** is ideal for use in wood or concrete patios, automobile showrooms, restaurant kitchens, garage floors, and many more. To use, stir contents of each container and mix together while stirring. Maintain a 2 to 1 ratio of Part A to Part B. Add equal parts water to the mixture and stir thoroughly. Let stand for 15 minutes before applying; set time takes approximately 2 hours. Surfaces to be treated should be clean, dry, and free of dirt and grease. Specific instructions for certain surfaces can be found on the label. Apply product with a brush, spray or roller and smooth to the desired finish. Allow 8 to 12 hours for proper curing. Mixed epoxy has a pot life of 2 hours at 72°F. Refer to the attached SDS for additional precautions. The information contained in this safety sheet is aimed at creating a guide for the selection and use of the product. However, we are not responsible for any use not recommended by ChemTron.

ChemTron  
3911 SW 47th AVE  
Davie, Florida 33314  
Tel: (954) 584 - 4530  
Fax: (954) 584 - 4531  
[www.ChemTron.com](http://www.ChemTron.com)

